

Technical Data Sheet

AWAZEL DESERT SHIELD 40200

4 mm thick, App modified bituminous membrane, reinforced with 200 gm/m² non woven polyester mat, complies with the requirements of ASTM D 6222 Type II, Grade S, UEAtc MOAT 30, CGSB 37-GP-56 M & DIN 52133

Description

High Performance Polymer (APP) modified bituminous membrane, reinforced with 200 g/m² non woven polyester mat. The polyester combines high tensile strength with an elongation above 40 %. The specially used polymer modifier has a great resistance to Ultra-Violet radiation.

Features

- Durable and easy to apply
- High flexibility at low temperature and stable at high temperature
- Remarkable resistance to aggressive attack of salts and chemicals
- High tensile strength and elongation
- Excellent tear and puncture resistance

Function

Used as double layers for tanking in basements or single or double layers for waterproofing of roofs. A single layer followed by a layer of mineral surfaced membrane (DS40200M) should be used for exposed roofs.

Instructions for Application

The membrane can be installed fully bonded or loose-laid by torch welding. The substrate should be cleaned and primed with AWAZEL PRIMER D 41 and allowed to dry. Torching should be done by skilled labor and should be controlled so that only the PE film is melted and the asphalt coating is softened sufficient to bond the membrane. All lap joints should be smoothed and sealed using a heated round-nosed trowel. The heat of the gas flame should be applied to the trowel. In

loose-laid applications, only the lap joints, areas around penetrations (pipes etc.), upstands and a 30 cm wide strip around the perimeter of the work should be fully bonded. Upstands and flashings should be installed using 1 M wide pieces cut from the length of the roll. (The overlap joints should be 5 to 10 cm at the sides and 15 cm at the end)

Coverage

1.12m per layer for flat surfaces

Health & Safety

All safety measures should be taken during applications. Fire extinguishers should be available in the site. Labor should wear personnel protective tools such as gloves and goggles during application.

Packing

It is produced in rolls of 1 x 10 meters; The rolls are palletized and shrink-wrapped.

Surfacing

Standard surfacing is P.E. Film on top bottom sides. Different combination of to surfacing are available upon request such as Sand, coloured minerals, etc...

Storage & Material Handling

The rolls should always be stored vertically in a shaded area. Normally the pallets should not be stacked one over the other. However, if a wooden board is used in between, two pallets may be stacked one over the other.

AWAZEL DESERT SHIELD 40200

4 mm thick, APP modified bituminous membrane, reinforced with non woven polyester mat, complies with the requirements of ASTM D 6222 Type II, Grade S, UEAtc MOAT 30, CGSB 37-GP-56M & DIN 52133

TECHNICAL DATA

Properties	Typical Results	Test Method
Roll Size, m	10 x 1	UEAtc M.O.A.T. 30
Nominal Thickness, mm	4.0	ASTM D 5147 UEAtc M.O.A.T. 30
Nominal Unit Weight, kg/m ²	4.0	UEAtc M.O.A.T. 30
Carriers weight, g/m ² (polyester)	200	UEAtc M.O.A.T. 30
Coating Asphalt : Type Softening Point (R&B), °C Penetration at 25 °C, 0.1 mm	APP Modified Asphalt >150 15 - 30	ASTM D 36 ASTM D 5
Tensile Strength, N/5cm	*	
Longitudinal	1,000	UEAtc M.O.A.T. 30
Transversal	800	ASTM D 5147
Elongation, %:		
Longitudinal	45 **	UEAtc M.O.A.T. 30
Transversal	50	ASTM D 5147
Tear Resistance, N :		
Longitudinal	450	ASTM D 5147
Transversal	400	ASTM D 4073
Lap Joint Strength, N/5cm		
Longitudinal	>1,000	UEAtc M.O.A.T. 30 & 27
Transversal	>800	
Load Strain Product:		
Longitudinal	45,000	CGSB-37 GP 56 M
Transversal	40,000	
Cold Flexibility at 0 to -5 °C	No Cracking	ASTM D 5147 UEAtc M.O.A.T. 30
Heat Resistance at 135 °C	No Flowing	ASTM D 5147 UEAtc M.O.A.T. 30
Resistance to Waterpressure, 2 bar (29 psi)	No Leakage	DIN 52123
Water Absorption, % (BSP)	<3.2	ASTM D 5147
Puncture Resistance	Static: L4 Dynamic : I4	UEAtc M.O.A.T. 27
Resistance to Aging after 2000 hours (Accelerated Weathering Tester)	No deterioration	ASTM D 4799

Note : The above shown technical data are typical results obtained, to the best of our knowledge, from our quality control records, extra details can be provided upon request

*. In accordance to the UEAtc standard, a variation of 20 % is expected.

**.. In accordance to the UEAtc standard, a variation of 15 % is expected.